

Appl. No. 09/980,225
Amdt. Dated December 16, 2003
Reply to Office Action of October 23, 2003

Amendments to the Claims:

This listing will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Claim 1 (currently amended): A molding material for use with carbon dioxide refrigerant, which comprises chlorinated polyethylene having a chloride content of 25-47% by ~~weight~~; weight and a coupling agent selected from the group consisting of vinylic, epoxy or methacryloxy silane coupling agents.

Claim 2 (previously presented): A molding material for use with carbon dioxide refrigerant according to claim 1, wherein the chlorinated polyethylene is used as a blend with vinyl chloride-based resin.

Claim 3 (previously presented): A molding material for use with carbon dioxide refrigerant according to claim 1, wherein an inorganic filler is further contained.

Claim 4 (canceled)

Appl. No. 09/980,225
Amdt. Dated December 16, 2003
Reply to Office Action of October 23, 2003

Claim 5 (previously presented): A molding material for use with carbon dioxide refrigerant according to claim 1, wherein 1-10 parts by weight of an organic peroxide is further contained on the basis of 100 parts by weight of the chlorinated polyethylene or its blend with the vinyl chloride-based resin.

Claim 6 (canceled)

Claim 7 (canceled)

Claim 8 (previously presented): A molding material for use with carbon dioxide refrigerant according to claim 2, wherein an inorganic filler is further contained.

Claim 9 (previously presented): A molding material for use with carbon dioxide refrigerant according to claim 2, wherein 1-10 parts by weight of an organic peroxide is further contained on the basis of 100 parts by weight of the chlorinated polyethylene or its blend with the vinyl chloride-based resin.

Claim 10 (previously presented): A molding material for use with carbon dioxide refrigerant according to claim 4, wherein 1-10 parts by weight of an organic peroxide is further contained on

Appl. No. 09/980,225
Amdt. Dated December 16, 2003
Reply to Office Action of October 23, 2003

the basis of 100 parts by weight of the chlorinated polyethylene or its blend with the vinyl chloride-based resin.

Claims 11-14 (canceled)